آدرس: اصفهان، شهرک صنعتی مبارکه، فاز دوم، خیابان دهم، پلاک ۹
تلفن: ۳۴۰۱ ۲۳۷ ۳۱۵-۰۹۸+
دورنگار: ۳۱۶۹ ۲۳۷ ۳۱۵-۰۹۸+
www.abnilshimi.com
E-mail: info@abnilshimi.com

ABNIL PRODUCTS

SPECIFICATION

		SERIES	Viscosity (cP)	Solid	pH	Density (gr/cm³)	MFFT (°C)	Tg (°C)
Vinyl Acetate Homopolymer Emulsion	H	H-21	(300-360)*10³	50±1	4-5	1.05±0.08	16	+30
		H-77	(280-320)*10³	50±1	4-5	1.05±0.08	16	+36
		H-101	(60-70)*10³	40±1	4-5	1.05±0.08	<1	-
		H-104	(2.5-4.5)*10³	38±1	3.5-4	1.05±0.08	11	-
		H-213	40-50	50±1	4-5	1.05±0.08	16	+30
		HM-21	(180-220)*10³	50±1	3-4	1.05±0.08	16	+30
		HM-21/1	200-400	50±1	3-4	1.05±0.08	16	+30
		HM-21/2	(10-40)*10²	50±1	3-4	1.05±0.08	16	+30
		HM-21/4	(14-20)*10²	49±1	3-4	1.05±0.08	13	+15
		HM-544	(100-150)*10³	51±1	3-4	1.05±0.08	12	-
		HB-105	150-200	49±1	5-6	1.05±0.08	14	+20
		HC-17	(170-220)*10³	52±1	6.5-7.5	1.2±0.05	16	-
		PHP-24	(255-275)*10³	50±1	4-5	1.05±0.08	16	+32
Vinyl Acrylic Emulsion	NILCO	NILCO-208	(220-250)*10³	51±1	4-5	1.05±0.08	10	+15
		NILCO-210	(54-56)*10³	50±1	4-5	1.05±0.08	13	+6
		NILCO-211	(20-40)*10³	50±1	4-5	1.05±0.08	13	+6
		NILCO-215	(65-68)*10³	50±1	4-5	1.05±0.08	5	-12
		NILCO-220	(17-20)*10³	51±1	4-5	1.05±0.08	<1	-20
		NILCO-312	(10-25)*10³	52±1	4-5	1.05±0.08	8	+12
		NILCO-312/T	(10-25)*10³	52±1	4-5	1.05±0.08	8	+12
		NILCO-625/4	(20-30)*10³	50±1	4-5	1.05±0.08	<1	+10
	NILTEX	NILTEX-544	(23-25)*10³	51±1	3-4	1.05±0.08	11	-
		NILTEX-546	(105-125)*10³	51±1	3-4	1.05±0.08	10	-
		NILTEX-550	(200-250)*10³	49±1	5-6	1.05±0.08	10	0
Acrylic Emulsion	BINAB	BINAB-40	80-150	40±1	5-6	1.02±1.06	<1	-10
		BINAB-400/S	(1.5-2.5)*10³	40±1	7-8	1.05±0.08	<1	0
		BINAB-40P	(30-40)	40±1	7-8	1.02±1.06	<1	-3
		BINAB-310/ST	(4-8)*10³	45±1	7-8	1.05±0.08	<1	-
	NILAB	NILAB-115	(30-40)*10³	51±1	7.5-8.5	1.05±0.08	20	+15
		NILAB-135	(9.5-10.5)*10³	51±1	7.5-8.5	1.05±0.08	30	+35
		NILAB-203S	(4-8)*10³	50±1	7-8	1.05±0.08	6	-3
		NILAB-235S	(8-10)*10³	50±1	7-8	1.05±0.08	<1	-35
		NILAB-240	(2.5-3.5)*10³	55±1	2-3	1.05±0.08	<1	-40
		NILAB-308/RC	(2.5-3.5)*10³	50±1	7-8	1.05±0.08	10	+5
		NILAB-310S	(8-12)*10³	50±1	7-8	1.05±0.08	15	+10
		NILAB-315P	(3.5-4.5)*10³	50±1	7-8	1.05±0.08	16	+15
		NILAB-315/PRC	(2-3)*10³	35±1	7-8	1.05±0.08	<1	-5
		NILAB-318S	(3.5-4.5)*10³	50±1	7-8	1.05±0.08	20	+18
		NILAB-318/TA	30-60	35±1	7-8	1.05±0.08	<1	+10
		NILAB-322S	(2.5-3.5)*10³	50±1	7-8	1.05±0.08	24	+22
		NILAB-330P	(6-10)*10³	50±1	7-8	1.05±0.08	28	+30
		NILAB-345P	80-150	45±1	7-8	1.05±0.08	50	+45
		NILAB-350S	80-150	45±1	7-8	1.05±0.08	55	+50

APPLICATION

Textile Industries		Building Industries			Wood & Cellulose					Painting Industries			Food Industries			Nonwoven Industries
Sizing	Textile Printing Binder	Insulation & Roof Coating	Tile Adhesive	Concrete Adhesive	Pressure-sensitive Adhesive	Live Adhesive: Non Effective Adhesive	Live Adhesive: Plastic Surfaces Adhesive	Thermal Adhesives	Labels Adhesive	Paints & Coatings For Internal Surfaces	Outside Paint & Coating	Marine paint	Printing primer For Aluminium Foil	printing primer	Food Grade Coating	
●			●	●	●											●
●																●
					●											
					●											
●																●
●			●	●	●											●
●					●											●
●					●											●
●					●											●
●																●
●																●
●																●
●					●											●
●			●		●											●
			●	●	●					●					●	
●					●	●				●						●
●			●						●							●
		●								●	●				●	
				●						●	●					
●																●
●																●
	●															
	●															
	●															
														●		
					●		●		●	●						
					●		●	●	●							
										●		●				
		●		●						●	●					
		●	●	●												
		●		●						●						
			●													
										●						
													●			
●																●
●																●